



# manufacturing parameters for curved toughened glass

**please be aware that all curved toughened will have flats of 100mm to 150mm.**

This will be more noticeable on glass bent to a tight radius than it will be on glass bent to a shallower radius.

Within the following guidelines the tolerance will be + or - half the glass thickness.

Maximum angle 90°

## *up to 1200 girth and 3450 length*

material	minimum rad	minimum girth	minimum length
4mm	550	350	100
5mm	550	350	100
6mm	660	350	100
8mm	880	350	100
10mm	1100	350	100
12mm	1320	350	100
15mm	1650	350	100
19mm	2090	350	100

Queens Mill Road  
Lockwood  
Huddersfield  
West Yorkshire  
HD1 3PG  
England

t + 44 (0) 1484 517010  
f + 44 (0) 1484 517050

e [sales@n-gn.co.uk](mailto:sales@n-gn.co.uk)  
w [www.glassbending.co.uk](http://www.glassbending.co.uk)

Reg. No. 5719519  
VAT No. 878033306



***up to 2500 girth and 3450 length***

material	minimum rad	minimum girth	minimum length
5mm	550	350	100
6mm	660	350	100
8mm	880	350	100
10mm	1100	350	100
12mm	1320	350	100
15mm	1650	350	100
19mm	2090	350	100

***up to 3150 girth and 5000 length***

material	minimum rad	minimum girth	minimum length
5mm	1320	100	500
6mm	1320	100	500
8mm	1320	100	500
10mm	1320	100	500
12mm	1320	100	500
15mm	1650	100	500
19mm	2090	100	500

Queens Mill Road  
Lockwood  
Huddersfield  
West Yorkshire  
HD1 3PG  
England

t + 44 (0) 1484 517010  
f + 44 (0) 1484 517050

e [sales@n-gn.co.uk](mailto:sales@n-gn.co.uk)  
w [www.glassbending.co.uk](http://www.glassbending.co.uk)

Reg. No. 5719519  
VAT No. 878033306

It is sometimes possible to work outside these guidelines as follows, you should however check with our technical department first, e.g.:-

- Greater than 90° angle
- Less than minimum quoted radius
- Longer than maximum quoted length

All bends manufactured outside the guidelines require increased tolerance of + and - half the glass thickness.

Queens Mill Road  
Lockwood  
Huddersfield  
West Yorkshire  
HD1 3PG  
England

t + 44 (0) 1484 517010  
f + 44 (0) 1484 517050

e [sales@n-gn.co.uk](mailto:sales@n-gn.co.uk)  
w [www.glassbending.co.uk](http://www.glassbending.co.uk)

Reg. No. 5719519  
VAT No. 878033306